


**CH-38-1.0-0.8  
Thermoelectric Module  
(Peltier Module)  
Specifications**

	Material Specifications (27 °C hot side temperature)	Material Specifications (50 °C hot side temperature)
Vmax (V)	4.7	5.2
I <sub>max</sub> (A)	5.8	5.8
Q <sub>max</sub> (W)	16.8	18.4
DT <sub>max</sub> (°C)	69	78
Operation/storage temperature	-40 °C to +80 °C	

Module *material* specifications are nominal values based on the hot-side temperature indicated. Thermoelectric material parameter tolerance is +/-10%.

In no case should the module temperature be allowed to exceed its maximum operation/storage temperature.

Please review all product and technical information, *Thermoelectric Module Mounting Procedure*, parameter definitions, FAQ's, and ordering information posted on our website before purchasing or using this product.



**Optional Features and Notes:**

Add "P" to part number for sealing module with epoxy potting.





Outer Diameter, OD (mm)	24 +0.5/-0.2
Inner Diameter, ID (mm)	9.8 +0.2/-0.5
Height, H (mm)	3.1 ±0.05
Flatness, F (mm)	0.02
Parallelism, P (mm)	0.03
Wire Size, WS (mm <sup>2</sup> )	0.34
Wire Length, WL (mm)	120

Performance graphs include thermal resistance of substrates.





RoHS Compliant  
Directive 202/95/EC







1590 Keane Drive, Traverse City, MI, 49696-8257 USA  
PH: 231-929-3966 FAX: 231-929-4163 email: cool@totech.com







Unpotted CH-38-1.0-0.8 at a hot-side temperature of 30 °C







Potted CH-38-1.0-0.8 at a hot-side temperature of 30 °C







Unpotted CH-38-1.0-0.8 at a hot-side temperature of 50 °C



Potted CH-38-1.0-0.8 at a hot-side temperature of 50 °C



Unpotted CH-38-1.0-0.8 at a hot-side temperature of 70 °C



Potted CH-38-1.0-0.8 at a hot-side temperature of 70 °C