


**TE-83-1.0-2.5
Thermoelectric Module
(Peltier Module)
Specifications**

	Material Specifications (27 °C hot side temperature)	Material Specifications (50 °C hot side temperature)
Vmax (V)	10.4	11.5
I _{max} (A)	1.9	1.9
Q _{max} (W)	12.0	13.2
DT _{max} (°C)	70	79
Operation/storage temperature	-40 °C to +80 °C	

Module *material* specifications are nominal values based on the hot-side temperature indicated. Thermoelectric material parameter tolerance is +/-10%.

In no case should the module temperature be allowed to exceed its maximum operation/storage temperature.

Please review all product and technical information, *Thermoelectric Module Mounting Procedure*, parameter definitions, FAQ's, and ordering information posted on our website before purchasing or using this product.



Width, A (mm)	22 +0.5/-0.2
Width, B (mm)	19 +0.5/-0.2
Height, H (mm)	4.8 ±0.05
Flatness, F (mm)	0.02
Parallelism, P (mm)	0.03
Wire Size, WS (mm ²)	0.2
Wire Length, WL (mm)	120

Optional Features and Notes:





Add "P" to part number for sealing module with epoxy potting.

Performance graphs include thermal resistance of substrates.





RoHS Compliant







1590 Keane Drive, Traverse City, MI, 49696-8257 USA
PH: 231-929-3966 FAX: 231-929-4163 email: cool@totech.com







Unpotted TE-83-1.0-2.5 at a hot-side temperature of 30 °C







Potted TE-83-1.0-2.5 at a hot-side temperature of 30 °C







Unpotted TE-83-1.0-2.5 at a hot-side temperature of 50 °C



Potted TE-83-1.0-2.5 at a hot-side temperature of 50 °C



Unpotted TE-83-1.0-2.5 at a hot-side temperature of 70 °C



Potted TE-83-1.0-2.5 at a hot-side temperature of 70 °C